Coating Specification Sheet



A corrosion resistant silicon barrier coating ideal for acidic, oxidative, and high purity environments.

Overview

Silcolloy® (patent info at www.silcotek.com/IP) is a chemically protective, corrosion resistant, multi-layered barrier of amorphous silicon. Applied via chemical vapor deposition (CVD), Silcolloy® is the ideal choice for protecting stainless steels, exotic metals, glass, ceramics and other alloys from corrosive attack or for preventing unwanted compounds from entering the process stream.

Key Applications and Benefits

- 3D non-line-of sight process coats all complex geometries including designs with high aspect ratios and small orifices.
- Achieve exotic material performance at a fraction of the price.
- Fight corrosion with a non-reactive, pure barrier.





Semiconductor



Stack & Flare

Chemical Process

Oil & Gas/Refining

Silcolloy® Specifications

| Coating Structure: | Hydrogenated amorphous silicon (a-Si:H) | |
|---------------------------------|---|---|
| Deposition Process: | Thermal chemical vapor deposition (not plasma-enhanced) | |
| Maximum Temperature: | 1410° C* | |
| Substrate: | Compatability: Size: Geometry: | Stainless steel, exotic alloys, ceramics Up to 78" (198 cm) Any shape, including complex geometrics |
| Typical Thickness: | 180 - 800nm | |
| Hydrophobicity (contact angle): | ≥40° | |
| Allowable pH Exposure: | 0 - 8 | |

#SPEC-SILCOLLOY *Contact technical service